

| PRODUCT NAME    | Dischargeability | Solubility | Fatness Properties |      |              |         |     |     |
|-----------------|------------------|------------|--------------------|------|--------------|---------|-----|-----|
|                 |                  |            | Light              | Wash | Perspiration | Rubbing |     |     |
|                 |                  |            |                    |      |              | Dry     | Wet |     |
| <b>DYDIRECT</b> |                  |            |                    |      |              |         |     |     |
| YELLOW PG CONC  |                  | P          | 50                 | 5-6  | 4            | 3-4     | 4   | 4   |
| YELLOW RL       |                  | P          | 80                 | 5-6  | 3-4          | 3       | 4-5 | 3   |
| YELLOW BGT-N    |                  | G          | 60                 | 4    | 4-5          | 4-5     | 5   | 4-5 |
| ORANGE 2GL      |                  | F          | 100                | 6-7  | 4            | 4       | 4-5 | 3-4 |
| SCARLET F2G     |                  | P          | 50                 | 3-4  | 4-5          | 4       | 3-4 | 3   |
| SCARLET LB      |                  | F          | 60                 | 4-5  | 4-5          | 4-5     | 5   | 4   |
| SCARLET 4BS     |                  | G          | 40                 | 2-3  | 4            | 4-5     | 4-5 | 2   |
| RED F3B         |                  | F          | 50                 | 5    | 4            | 4       | 5   | 3-4 |
| ROSE FR         |                  | G          | 100                | 3-4  | 4-5          | 4       | 4   | 3   |
| RED BWS         |                  | P          | 100                | 5-6  | 4-5          | 3-4     | 4-5 | 3-4 |
| VIOLET 4BD      |                  | G          | 50                 | 6    | 4            | 4-5     | 4-5 | 4   |
| TURQ. BLUE FBL  |                  | P          | 60                 | 5-6  | 3            | 2       | 3-4 | 2-3 |
| BLUE GL         |                  | G          | 50                 | 5    | 4-5          | 4       | 4   | 3   |
| BLUE FFRL       |                  | G          | 40                 | 6    | 4            | 5       | 4-5 | 3   |
| BLUE 4BL H-CONC |                  | G          | 50                 | 5    | 4-5          | 4-5     | 5   | 3   |
| BLUE GNR        |                  | G          | 80                 | 5-6  | 5            | 4-5     | 4   | 3-4 |
| BLUE B2R        |                  | G          | 100                | 4-5  | 5            | 4       | 4   | 3-4 |
| GREEN NDF       |                  | G          | 100                | 4-5  | 4-5          | 4       | 5   | 4   |
| KHAKI G         |                  | G          | 50                 | 5    | 4-5          | 4-5     | 5   | 4   |
| BROWN AGL       |                  | P          | 70                 | 5-6  | 4-5          | 4-5     | 4   | 3   |
| BROWN GTL       |                  | F          | 40                 | 6-7  | 5            | 4-5     | 4   | 3   |
| BROWN GR        |                  | G          | 60                 | 4-5  | 4            | 4-5     | 4-5 | 4   |
| BROWN LB        |                  | F          | 35                 | 6    | 5            | 4-5     | 4-5 | 4   |
| GREY L4G        |                  | P          | 40                 | 5    | 4-5          | 4       | 4-5 | 4   |
| BLACK VSF 800%  |                  | G          | 50                 | 4    | 3-4          | 4-5     | 4   | 3   |
| BLACK VSF 1200% |                  | G          | 40                 | 4-5  | 3-4          | 4-5     | 4   | 3   |
| BLACK VSF 1600% |                  | G          | 30                 | 5    | 3-4          | 4-5     | 4   | 3   |